## LaserfocusWorld

International Resource for Technology and Applications in the Global Photonics Industry

## **newS**breaks

## Stress-reduced solar-blind AlGaN-based FPA is crack-free

Focal-plane arrays (FPAs) that operate in the solar-blind spectral region (created by the absorption of light below 290 nm by atmospheric ozone) have uses in covert non-line-of-sight and other forms of freespace communications, as well as UV spectroscopy, flame detection, and many other applications. With their extremely high rejection of the non-solar-blind

log (responsivity)
(mA/W)
100
100
10
20
250 300 350 400
Wavelength (nm)
250 300 350 400
Wavelength (nm)

spectrum, aluminum gallium nitride (AlGaN)-based structures are potentially excellent photodetecting candidates for solar-blind FPAs. However, this type of structure is difficult to fabricate without the formation of cracks. Manijeh Razeghi's group at Northwestern University (Evanston, IL) has developed a solution to this problem by patterning an AlN tem-

plate into isolated mesas that help reduce cracks in the AlGaN-based structure that is then grown.

Square mesas 26 µm on a side are etched partway into the AIN in a 2D square array with a 30 µm period by etching the AIN to a 300 nm depth that separates the mesas so that stress in one does not affect others, but is not so deep that lateral conductivity suffers. The rest of the FPA is then fabricated, ensuring that the

Focal-plane arrays that operate in the solar-blind spectral region have uses in covert non-line-of-sight and other forms of free-space communications.

conduction layer is continuous between mesas. At a 279 nm wavelength, two FPA samples had external quantum efficiencies (EQEs) of 38% and 27%, respectively, and responsivities of 86.2 and 60.9 mA/W, respectively, for zero bias; and 57% and 44%, respectively, and 129.4 mA/W and 99.4 mA/W, respectively, for 5 V reverse bias. Contact Manijeh Razeghi at razeghi@eecs.northwestern.edu.